

CONTENTS

	Page
ACKNOWLEDGEMENT	iii
ABSTRACT (English)	iv
ABSTRACT (Thai)	vi
LIST OF TABLES	xi
LIST OF FIGURES	xiii
ABBREVIATIONS	xvii
CHAPTER 1 : INTRODUCTION	1
1.1 Biodegradable Polymers	1
1.2 The Need for Biodegradable Materials	3
1.3 The Requirements of a Biodegradable Material	5
1.4 The Use of Polymer as Surgical Sutures	6
1.4.1 Absorbable Sutures	6
1.4.2 Non absorbable Sutures	7
1.5 Monofilament Versus Multifilament Sutures	8
1.5.1 Monofilament	8
1.5.2 Multifilament	9
1.5.3 Comparison of Performance Characteristics in Surgery	9
1.6 Commercial Sutures	11
1.6.1 Polydioxanone: PDS Sutures	12
1.6.2 MAXON Sutures	14
1.6.3 MONOCRYL Sutures	17

	Page
CHAPTER 2 : POLYMER BIODEGRADATION	20
2.1 Mechanism of Biodegradation	20
2.1.1 Solubilization	20
2.1.2 Ionization Followed by Solubilization	21
2.1.3 Enzyme-Catalysed Hydrolysis	21
2.1.4 Simple Hydrolysis	22
2.2 The Phenomena of Biodegradation	22
2.2.1 Hydration	23
2.2.2 Strength Loss	24
2.2.3 Loss of Mass Integrity	24
2.2.4 Mass Loss (Solubilization)	24
2.3 Testing for Biodegradation	26
2.3.1 <i>In Vitro</i> Testing	26
2.3.2 <i>In Vivo</i> Testing	27
2.3.3 Clinical Trials	27
2.4 <i>In Vitro</i> Biodegradation Studies	28
2.4.1 Weight Loss	28
2.4.2 Polymer Morphology	29
2.4.3 Material Surface	31
2.4.4 Tensile Strength	32

	Page
CHAPTER 3 : A NEW BIODEGRADABLE POLYMER FOR USE AS AN ABSORBABLE MONOFILAMENT SUTURE	33
3.1 Poly(glycolide): PG	34
3.2 Poly(lactide): PL	36
3.3 Polycaprolactone: PCL	38
3.4 Terpolymers of Glycolide, L-Lactide and ϵ -caprolactone	40
3.5 Terpolymer Characterization	42
3.6 Fiber Processing and Fiber Characterization	43
3.6.1 Fiber Processing	43
3.6.2 Fiber Characterization	44
3.7 Aim of This Study	44
CHAPTER 4 : EXPERIMENTAL ASPECT	45
4.1 Chemicals, Apparatus and Instruments	45
4.1.1 Chemicals	45
4.1.2 Apparatus and Instruments	46
4.2 Instrumental Method	47
4.2.1 Dilute-Solution Viscometry	47
4.2.1.1 Dilute-Solution Viscosity Measurements	47
4.2.1.2 Definitions of Dilute-Solution Viscosity Terms	50
4.2.1.3 Determination of Intrinsic Viscosity	52
4.2.1.4 Intrinsic Viscosity	55
4.2.2 Differential Scanning Calorimetry	56
4.2.3 Scanning Electron Microscopy	58
4.2.4 Universal Mechanical Testing Machine	59

	Page
CHAPTER 5 : <i>IN VITRO</i> BIODEGRADATION	63
5.1 Experimental Procedure	63
5.1.1 Phosphate Buffer Saline (PBS) Immersion Medium (pH 7.40)	63
5.1.2 Sample Preparation	64
5.1.3 Sampling Procedure	66
5.2 Property Changes from Biodegradation	66
5.2.1 Weight Loss Profiles	66
5.2.2 Tensile Strength Profiles	73
5.2.3 Melting Point and Heat of Fusion Profiles	80
5.2.4 Stability of Phosphate Immersion Medium	88
5.2.5 Intrinsic Viscosity	91
5.2.6 Scanning Electron Microscopy	92
CHAPTER 6 : DISCUSSION AND CONCLUSIONS	98
6.1 Property Changes from <i>In Vitro</i> Biodegradation	98
6.2 A Mechanistic View of the Biodegradation Process	102
SUGGESTIONS FOR FURTHER WORK	108
REFERENCES	109
VITA	111

LIST OF TABLES

Table	Page
1.1 Some biodegradable polymers used in medicine	3
1.2 Suture materials used in surgery	7
1.3 Comparison of the properties of monofilament and multifilament absorbable sutures in surgery	10
1.4 Properties of poly(dioxanone) monofilament suture, size 00	13
1.5 Physical property comparison of size 2-0 absorbable sutures	18
2.1 Four stages of polymer degradation <i>in vivo</i>	23
4.1 Chemicals used in this research project	45
4.2 Apparatus and instruments	46
4.3 Definitions and nomenclature of dilute-solution viscosity quantities	50
5.1 Weights and %weight retentions of MONOCRYL sutures immersed in pH 7.40 phosphate buffer saline medium at $37.0 \pm 1.0^{\circ}\text{C}$	68
5.2 Weights and %weight retentions of MAXON sutures immersed in pH 7.40 phosphate buffer saline medium at $37.0 \pm 1.0^{\circ}\text{C}$	69
5.3 Weights and %weight retentions of PDS II sutures immersed in pH 7.40 phosphate buffer saline medium at $37.0 \pm 1.0^{\circ}\text{C}$	70
5.4 Weights and %weight retentions of PLCG fibers immersed in pH 7.40 phosphate buffer saline medium at $37.0 \pm 1.0^{\circ}\text{C}$	71

Table	Page
5.5 Tensile strengths and % tensile strength retentions of MONOCRYL, MAXON, PDS II and PLCG monofilament fibers immersed in a pH 7.40 phosphate buffer saline medium at $37.0 \pm 1.0^{\circ}\text{C}$	78
5.6 DSC melting peak data for the MONOCRYL, MAXON, PDS II and PLCG monofilament fibers immersed in pH 7.40 phosphate buffer saline medium at $37.0 \pm 1.0^{\circ}\text{C}$	85
5.7 Variation in pH of the phosphate buffer saline solutions containing the MONOCRYL, MAXON, PDS II and PLCG samples during the period of the biodegradation experiment	89
5.8 Intrinsic viscosities, $[\eta]$, and their % retentions for the PLCG fibers immersed in the pH 7.40 phosphate buffer saline solution at $37.0 \pm 0.1^{\circ}\text{C}$	91

LIST OF FIGURES

Figure	Page
1.1 The physical form of a melt-spun monofilament sutures	8
1.2 The physical form of a braided multifilament sutures	9
1.3 Synthesis of poly(dioxanone)	12
1.4 Average breaking strength retention, BSR of monofilament poly(dioxanone) suture following implantation in the subcutis of rats compared with the range of similarly derived data for multifilament (DEXON and VICRYL) suture. Data expressed as average percentage of original, unimplanted strength	14
1.5 Synthesis of poly(glycolide-co-trimethylene carbonate) (MAXON)	15
1.6 Comparison of poly(glycolic acid) (PGA) braided sutures and MAXON. The mean retention of strength as a percentage of package values after implantation into the subcutaneous tissues of rats is shown	16
1.7 Molecular structure of MONOCRYL	17
1.8 Average breaking strength of size 2-0 MONOCRYL, VICRYL, PDS II and Chromic Gut sutures as a function of implantation time in the subcutis of rats	19
2.1 Generic curves showing the sequence of polymer-molecular weight, strength and mass-reduction over time	25
2.2 The level of crystallinity of synthetic absorbable sutures upon <i>in vitro</i> hydrolysis in phosphate buffer	30

Figure	Page
3.1 Synthesis of poly(glycolide) (PG)	34
3.2 <i>In vitro</i> degradation of polyglycolide	35
3.3 Synthesis of poly(lactide) (PL)	36
3.4 <i>In vitro</i> degradation of poly(L-lactide)	37
3.5 Polymerization of PCL	38
3.6 <i>In vivo</i> degradation of absorbable sutures	39
4.1 Viscometer commonly used in polymer chemistry: (a) Ostwald viscometer (b) Ubbelohde viscometer	48
4.2 Schott-Gerate AVS300 Automatic Viscosity Measuring System	49
4.3 Reduced and inherent viscosity-concentration plots for a typical polymer sample	
4.4 The Perkin-Elmer DSC7 Differential Scanning Calorimeter	57
4.5 Photographs of the Lloyds LRX+ Universal Testing Machine used for fiber mechanical testing	60
4.6 Photographs of the bollard grips	61
5.1 Incubator used for the <i>in vitro</i> biodegradation experiment	65
5.2 Comparison of the weight loss profiles of the MONOCRYL, MAXON, PDS II and PLCG monofilament fibers during the period of the <i>in vitro</i> Biodegradation experiments	72

Figure	Page
5.3 Comparison of stress-strain curves of MONOCRYL sutures during the period of the <i>in vitro</i> biodegradation experiments	74
5.4 Comparison of stress-strain curves of MAXON sutures during the period of the <i>in vitro</i> biodegradation experiments	75
5.5 Comparison of stress-strain curves of PDS II sutures during the period of the <i>in vitro</i> biodegradation experiments	76
5.6 Comparison of stress-strain curves of PLCG fiber during the period of the <i>in vitro</i> biodegradation experiments	77
5.7 Tensile strength retention-time profiles for MONOCRYL, MAXON, PDS II sutures and the PLCG monofilament fibers immersed in a phosphate buffer saline medium of pH 7.40 at $37.0 \pm 1.0^{\circ}\text{C}$	79
5.8 Comparison of DSC thermograms of MONOCRYL sutures during the period of the <i>in vitro</i> biodegradation experiments	81
5.9 Comparison of DSC thermograms of MAXON sutures during the period of the <i>in vitro</i> biodegradation experiments	82
5.10 Comparison of DSC thermograms of PDS II sutures during the period of the <i>in vitro</i> biodegradation experiments	83
5.11 Comparison of DSC thermograms of PLCG fiber during the period of the <i>in vitro</i> biodegradation experiments	84
5.12 Comparison of the melting point profiles of the MONOCRYL, MAXON, PDS II and PLCG monofilament fibers over the period of the <i>in vitro</i> biodegradation experiments	86

Figure	Page
5.13 Comparison of the heat of fusion profiles of the MONOCRYL, MAXON, PDS II and PLCG monofilament fiber over the period of the <i>in vitro</i> biodegradation experiments	87
5.14 Variation in pH of the phosphate buffer saline solution containing the MONOCRYL, MAXON, PDS II and PLCG samples during the period of the biodegradation experiments	90
5.15 The intrinsic viscosity loss profiles of the PLCG fiber over the period of the biodegradation experiments	92
5.16 SEM micrographs of the MONOCRYL sutures after immersion in the pH 7.40 phosphate buffer at 37.0°C for various times from 0-3 weeks (Magnification = x 140-200)	93
5.17 SEM micrographs of the MAXON sutures after immersion in the pH 7.40 phosphate buffer at 37.0°C for various times from 0-16 weeks (Magnification = x 160-200)	94
5.18 SEM micrographs of the PDS II sutures after immersion in the pH 7.40 phosphate buffer at 37.0°C for various times from 0-18 weeks (Magnification = x 120-180)	95
5.19 SEM micrographs of the PLCG fiber after immersion in the pH 7.40 phosphate buffer at 37.0°C for various times from 0-6 weeks (Magnification = x 120-180)	96
6.1 Simple hydrolysis of a poly- α -ester	103
6.2 The various physico-chemical processes involved in suture absorption	105

ABBREVIATIONS

T_c	crystallization temperature
T_g	glass transition temperature
T_m	melting temperature
T_d	degradation temperature
DSC	differential scanning calorimetry
TG	thermogravimetry
SEM	scanning electron microscopy
rh	relative humidity
$^{\circ}\text{C}$	degrees Celcius
K	degrees Kelvin
MPa	megapascal
ΔH_f	heat of fusion