ชื่อเรื่องวิทยานิพนธ์

การพัฒนาวิธีการเตรียมทางเคมีในสารละลายและ การวิเคราะห์สารตัวนำยวดยิ่งอุณหภูมิวิกฤตสูง ระบบบิสมัท

ชื่อผู้เขียน

นายเสนีย์ เครือเนตร

วิทยาศาสตรมหาบัณฑิต

สาขาวิชาเคมี

คณะกรรมการสอบวิทยานิพนธ์

ผศ.ดร.สายสุนีย์ เหลี่ยวเรื่องรัตน์ ประธานกรรมการ
รศ.ดร.เสาวณีย์ รัตนพานี กรรมการ
รศ.ดร. วิจิตร รัตนพานี กรรมการ

## บทคัดย่อ

ได้เตรียมสารตัวน้ำยวดยิ่งระบบบิสมัทโดยวิธีการเตรียมเป็นสารละลายแล้วระเหยแห้ง และแทนที่บิสมัทในสารตัวอย่างด้วยตะกั่วอัตราส่วนต่างๆกันตั้งแต่ 0.1 – 1.8 ได้ปรับปรุงวิธี การเตรียมโดยในขั้นตอนการบดสารก่อนอัดเม็ด ได้บดผสมผงของสารตัวน้ำยวดยิ่งจำนวนเล็ก น้อยลงไปในทุกอัตราส่วนที่เตรียมขึ้น จากนั้นนำไปอัดเม็ดและเผาที่อุณหภูมิ 855 องศา เซลเซียส นาน 3 ชั่วโมง แล้วลดอุณหภูมิลงเป็น 850 องศาเซลเซียส นาน 30 ชั่วโมง ได้วัดหา อุณหภูมิวิกฤตสากสารตัวนำยวดยิ่งที่เตรียมได้โดยวิธี four-point probe ได้อุณหภูมิวิกฤตสูง สุด 112.9 เคลวิน ที่อัตราส่วน บิสมัท : ตะกั่ว : แคลเซียม : สทรอนเซียม : ทองแดง เป็น 1.8 : 0.2 : 2 : 3 และองค์ประกอบต่างๆ ในสารตัวนำยวดยิ่งที่เตรียมได้จะนำไปวิเคราะห์หา บริมาณด้วยเทคนิกทางเคมีที่เหมาะสมดังนี้ ตะกั่ว บิสมัท และ ทองแดง วิเคราะห์ด้วยเทคนิก โวลแทมเมทรี (voltammetry) ด้วย mode DPASV แคลเซียมและสทรอนเซียมวิเคราะห์ด้วย เทคนิก erตอมมิกซ์สเปกโทรโฟโทเทรี โครงสร้างของสารตัวนำยวดยิ่งที่เตรียมได้จะศึกษาด้วย เทคนิก FT-IR และ XRD จากข้อมูลทางเอกซ์เรย์พบว่าสารตัวนำยวดยิ่งที่ได้มีโครงสร้างเป็น ออร์โทรอมบิค (Orthorhombic) ซึ่งมีโครงสร้างแลททิส a, b และ c เท่ากับ 5.398 A° 26.990 A° และ 30.739 A° ตามลำดับ

Thesis Title Development of the Wet Chemical Method for

Preparation and Analysis of High T<sub>c</sub> Superconductor

Bismuth System

Author Mr. Senee Kruanetr

M.S. Chemistry

Examining Committee Asst. Prof. Dr. Saisunee Liawruangrath Chairman

Assoc. Prof. Dr. Sawanee Rattanaphani Member

Assoc. Prof. Dr. Wijit Rattanaphani Member

## **Abstract**

The high Tc superconductors of the bismuth system, with the mole ratios of 2:2:2:3 was prepared via evaporation to dryness method and Bi atom in superconductor samples was replaced with various amounts of Pb 0.1 - 1.8 in mole ratio. The preparation method was developed by grounding small amounts of superconducting powder and mixed thoroughly with the superconductor powder samples. Subsequently, the powder sample was pressed into disk-shaped pellets, sintered at 855 °C for 3 hrs. and the temperature was decreased to 850 °C for 30 hrs. and cooled down to room temperature. The Tc of prepared superconducting samples was measured by four-point probe method. It was found that the prepared superconductor with the ratio of Bi:Pb:Ca:Sr:Cu 1.8:0.1:2:2:3 gave the highest Tc (112.9 K). The metal contents in the superconducting samples were determined by the appropriate techniques Pb, Bi and Cu were determined by voltammetric technique on DPASV mode, Ca and Sr were determined by atomic absorption spectrophotometric technique. The structure of superconducting samples was studied by FT-IR and XRD. According to the XRD data, it was found that the structure of the superconducting samples was orthorhombic with its lattice parameter a, b, c of 5.398 A°, 26.990 A° and 30.739 A° respectively.